

ALPHA[®] TELECORE[®] PLUS

NO-CLEAN, CORED SOLDER WIRE

DESCRIPTION

ALPHA TELECORE PLUS is a low residue core solder designed for no-clean soldering applications that meet high SIR reliability and excellent spread characteristics. The unique blend of rosin and proprietary activators provide rapid wetting while leaving minimal, optically clear, completely inert residue.

FEATURES & BENEFITS

- *Fast wetting → Excellent for High Throughput.*
- *Good spread characteristics → Excellent Solder Joints Formation.*
- *Clear non-tacky residue → No-Clean Residues. Useful for all Applications.*
- *Provides good joint appearance → Makes Inspection easy.*

PRODUCT INFORMATION

Standard	Alloy Designation	Melting or Solidus / Liquidus Temp °C	Flux Amount
Proprietary	SACX Plus [®] 0307	217 - 228	2.2% & 3.3%
Proprietary	SACX Plus [®] 0807	217 - 226	2.2% & 3.3%
J-STD-006B	Sn96.5Ag3.0Cu0.5 (SAC305)	217 - 221	2.2%, 3.3%
J-STD-006B	Sn96.5Ag3.5	221	2.2%, 3.3%
J-STD-006B	Sn99.3Cu0.7	227	2.2%, 3.3%
J-STD-006B	Sn63Pb37	183	1.1%, 2.2%
J-STD-006B	Sn62Pb36Ag2	179	1.1%, 2.2%
J-STD-006B	Sn10Pb88Ag2	268 - 299	1.1%, 2.2%

* TELECORE PLUS may also be available in other or special alloys and flux amounts on request.

ALPHA® TELECORE® PLUS

NO-CLEAN, CORED SOLDER WIRE

APPLICATION

A soldered joint is formed by heating the parts to be soldered to a temperature in excess of the melting point of the alloy to be used – in hand soldering this is how a soldering iron is used. By feeding the cored wire onto the parts, the flux is able to flow and remove oxidized metal, while the solder creates a thin inter-metallic bond which becomes the solder joint.

Note the following tips:

- Use a soldering iron tip size and form to suit the operation: small tips for soldering large components may prevent the formation of a joint or slow the process down.
- Select a solder wire diameter to suit both the soldering iron tip and the parts/components to be soldered.
- Soldering iron systems should provide sufficient heat to satisfy the requirements of the points above.
- A typical solder tip temperature would be between 120°C and 160°C above the liquidus temperature of the alloy. The ideal temperature to use is dependent on how thermally demanding the assembly is.
- Cored solder wires can be provided in different grades of alloy so always ensures that you have selected the right grade for the application.
- Do not overheat as this causes an increase in the depth of the inter-metallic layer, which in turn weakens the joint.

If you choose to use a liquid rework flux, ALPHA NR205 Flux is recommended to provide the optimal combination of high long-term reliability and low residue level. NR205 Flux is available in Alpha's Write Flux Pens for precision flux application.

TECHNICAL DATA

Physical Properties	Typical Values
Rosin Grade:	WW per Fed Spec. LL-R-626
Rosin Softening Point:	71°C (160°F)
Halide Content:	< 1,000ppm per JIS Z 3197
Classification:	ROL0 per ANSI/J-STD-004 ROL1 per IPC J-STD-004A/B
Shelf Life / Storage Temperature	36 months / 10°C - 40°C

ALPHA® TELECORE® PLUS

NO-CLEAN, CORED SOLDER WIRE

Electrical Reliability Test	Requirements	Results
Surface Insulation - Bellcore Test (GR-78-CORE) - IPC J-Std 004A - IPC-J-Std 004B	- $1.0 \times 10^{11} \Omega$ minimum - $1.0 \times 10^8 \Omega$ minimum - $1.0 \times 10^8 \Omega$ minimum	PASS
Electromigration IPC J-Std 004B	SIR(initial)/SIR (Final) < 10	PASS

Chemical Reliability Test	Requirements	Results
Copper Mirror Test (IPC-TM-650- 2.3.32)	No evidence of mirror breakthrough	PASS
Copper Corrosion Test (IPC-TM-650-2.6.15)	No evidence of corrosion	PASS

SAFETY

Observe standard precautions for handling and use. Use in well ventilated areas. DO NOT SMOKE during use.

ALPHA TELECORE PLUS cored solder wire is not considered toxic. However, its use in typical soldering applications will generate a small amount of decomposition and fumes. These fumes should be adequately exhausted / vented for operator safety and comfort. Consult the SDS for additional safety information. The most recent version of the SDS is available from alphaassembly.com.

STORAGE

ALPHA Cored Solder Wires should be stored in dry conditions and within a temperature range of 10°C to 40°C. When stored under these conditions the product shelf life is indefinite. However, Alpha guarantees the product shelf life for three years from the date of manufacture when stored in dry conditions and within 0°C to 40°C.

CONTINUED ON NEXT PAGE

ALPHA® TELECORE® PLUS

NO-CLEAN, CORED SOLDER WIRE

CONTACT INFORMATION

To confirm this is the most recent issue, please contact Alpha Assembly Solutions

AlphaAssembly.com

<p>North America 300 Atrium Drive Somerset, NJ 08873, USA 800.367.5460</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 01483.758400</p>	<p>Asia 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
---	---	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency directory assistance Chemtrec 1 - 800 - 424 - 9300.

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OR MERCHANTABILITY OR WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any product defective at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect and consequential damages that may result from use of the products under conditions, and agrees to exonerate, indemnify and hold harmless MacDermid Incorporated therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in infringement of any patent rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© Registered Trademark of MacDermid Performance Solutions. ™ Trademark of MacDermid Performance Solutions.
© Platform Specialty Products Corporation and its subsidiaries 2016.